





Casey Concrete

caseyconcrete.ca

198 x 298 mm (8 x 12 in.) BORDER STONE



-  NATURAL GREY
-  GRANITE
-  CHARCOAL
-  SAND-CHARCOAL
-  CASEY-MIX
-  EARTHBLEND



DE-ICING SALT DURABILITY MASS LOSS (max.):
 225 g/m² after 28 cycles, or 500 g/m² after 49 cycles

PLEASE NOTE:
 Products are made from natural material sources and therefore colour variations are common.
 Efflorescence is also a common occurrence with all concrete and concrete products.
 Efflorescence does not affect the quality of the product and will fade over time or can be removed with cleaning products.

PACKAGING

Pieces Per Pallet:	160 (60 mm); 128 (80 mm)
Weight Per Piece:	60 mm 8 kg (18 lbs) – 80 mm 10.7 kg (24 lbs)
Weight Per Pallet:	60 mm 1280 kg (2820 lbs)
Weight Per Pallet:	80 mm 1365 kg (3010 lbs)
Coverage Per Pallet:	103.3 sq. ft (60 mm); 82.6 sq. ft (80 mm)

DIMENSIONAL TOLERANCES:
 Meets the requirements of CSA A231.2 Concrete Pavers
 Length: -1 mm to +2 mm
 Width: -1 mm to +2 mm
 Height: -3 mm to +3 mm

AVAILABILITY:
 Available in smooth and stone textured top surface
 Available in 60 mm (2.4 in.) and 80 mm (3.2 in.) thickness

PHYSICAL PROPERTIES:
 Meets the requirements of CSA A231.2 Concrete Pavers
 Compressive Strength: Min 50 MPa @ 28 Days
 Absorption (%): 5.5% Maximum @ 28 Days
 Freeze/Thaw: Not exceed 1% weight loss

**DETAIL "A" SCALE 2.9:1
 ROTATED 90°**

