

NATURAL GREY



GRANITE



CHARCOAL



SAND-CHARCOAL




CASEY-MIX



EARTHBLEND

DETAIL "A" SCALE 2:1
ROTATED 90°



DE-ICING SALT DURABILITY MASS LOSS (max.):

225 g/m² after 28 cycles, or 500 g/m² after 49 cycles

PLEASE NOTE:

Products are made from natural material sources and therefore colour variations are common. Efflorescence is also a common occurrence with all concrete and concrete products. Efflorescence does not affect the quality of the product and will fade over time or can be removed with cleaning products.

AVAILABILITY:

Available in smooth top surface
Available in 60 mm thickness

PACKAGING

Pieces Per Pallet: 480
Weight Per Piece: 2.73 kg (6 lbs)
Weight Per Pallet: 1310 kg (2880 lbs)
Coverage Per Pallet: 103.3 sq. ft

DIMENSIONAL TOLERANCES:

Meets the requirements of CSA A231.2 Concrete Pavers
Length: -1 mm to +2 mm
Width: -1 mm to +2 mm
Height: -3 mm to +3 mm

PHYSICAL PROPERTIES:

Meets the requirements of CSA A231.2 Concrete Pavers
Compressive Strength: Min 50 MPa @ 28 Days
Absorption (%): 5.5% Maximum @ 28 Days
Freeze/Thaw: Not exceed 1% weight loss

